

Test Report No. <u>2891/17</u> Sassuolo, 31/03/17

## CENTRO DI RICERCA E SPERIMENTAZIONE PER L'INDUSTRIA CERAMICA

Requested by:	uested by: VIEW S.r.I. Via Monchio, 42/46 – 41042 FIORANO MODENESE (MO)								
For the sample:	Ceramic tiles of different sizes marked "Unglazed ceramic tiles - Serie GEA GRIP".								
On (date): 23/02/17		Date of receipt in laboratory (sample delivered by the client): 23/02/17							
Test date		From: 06/03/17	<i>To:</i> 06/03/17						

## EN ISO 10545-6 - Determination of resistance to deep abrasion (Unglazed tiles)

Test specimens	1A	1B	2A	2B	ЗA	3B	4A	4B	5A	5B
I, chord length (mm)	24,0	24,0	24,0	24,0	24,0	24,5	24,0	23,5	24,0	24,0
V, abraded volume (mm <sup>3</sup> )	116	116	116	116	116	123	116	109	116	116

Average volume, Vm (mm<sup>3</sup>):

116

Eng. Giordana Carani Technical approval



The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.

Via Martelli 26 40138 Bologna – Italy Tel. +39 051 534015 Fax +39 051 530085 Part. IVA 0094778-0375 centro.ceramico@centroceramico.it www.centroceramico.it Viale Valle d'Aosta 1 41049 Sassuolo (MO) – Italy Tel. +39 0536 802154 Fax +39 0536 800662